

Ronass Gloss Synthetic Enamels are based on alkyd resins and offered in a wide range of colours. These products offer excellent hiding power and flow, as well as ease of application. This product group is high gloss and allows for great gloss retention, excellent stability and durability with no yellowing or chalking. These products comply with National Iranian Standard ISIRI-1750. (Certificate No. 8600318654)

### USES AND SUITABLE PRIMERS

**Recommended Uses** Intermediate and finish coat for decorative coating systems on steel, wood, concrete and plaster surfaces.  
**Suitable Primers** Alkyd primers, pure or modified chlorinated rubber primers, synthetic primers, epoxy primers and cellulosic primers.

### CHEMICAL COMPOSITION

Type of Binder	Alkyd Resin	Solid Content	60 ± 5% By Weight
Number of Component(s)	1 Component		49 ± 3% By Volume
Curing Mechanism	Solvent Evaporation and Oxidation	Flash Point	38°C (100°F)

### PHYSICAL PROPERTIES

**Finish** Gloss  
**Colour** Wide range available according to the Ronass colour catalogue  
**Specific Gravity** 1.07 ± 0.10 gr/cm<sup>3</sup>

### APPLICATION DETAILS

**Surface Preparation** Concrete, Cement and Chalk Surfaces: All oil, grease, dirt, salts and other contaminants must be removed from the surface using fresh water or acid-washing. Rid the surface of any old paint that may have been applied, and use a suitable varnish to fill any cracks.  
Wood Surfaces: All oil, grease, dirt, old paint and other contaminants must be removed from the surface. Sand the surface to achieve the desired roughness and apply 1 to 2 layers of a suitable sealer to better protect against water and improve adhesion. After the sealer has dried, sand the surface to ready it for paint application.  
Steel Surfaces: All oil, grease, dirt and other contaminants must be removed from the surface. Use a sanding machine or wire brush if necessary, and use of a suitable primer such as 555 (Grey Synthetic primer) or 919 (Ronass Anti-Rust primer) is recommended.

**Theoretical Consumption** 110 gr/m<sup>2</sup> @ 50 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.009" – 0.015"	1.40 – 1.80 mm	---	---
	Pump Ratio	1 / 28	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	8 – 12% T-411	15 – 20% T-411	3 – 5% T-411	3 – 5% T-411

Film Thickness	Recommended		Minimum	Maximum
	Wet Film Thickness (µm)	105	60	145
Dry Film Thickness (µm)	50	30	70	

Drying Time	Surface Drying Time	Thorough Drying Time	Dry to Handle	Recoating Interval
	4 – 5 Hours	16 – 24 Hours	24 Hours	After 24 Hours

*\*Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits	Relative Humidity	Min. ---	Max. 85%
	Temperature	Min. +10°C	Max. +45°C
	Substrate Temperature*	Min. +10°C	Max. +50°C

*\*Please note that the substrate temperature should be at least 5°C above the dew point*

**Recommendations** Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-411.

### PACKING, STORAGE AND SAFETY

**Packing** 1 Lit | 4 Lit | 20 Lit  
**Storage Conditions** To be stored in cool and dry conditions within a temperature range of +40°C maximum in original sealed containers.  
**Shelf Life** At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.  
**Safety** This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach.  
 Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.