

| Special one-component, du  | urable, quick drying protecti  | ive primer with excellent   | adhesion and anti-corr         | rosive properties.     |                               |  |
|--|--|---|--------------------------------|------------------------|-------------------------------|--|
| USES AND SUITABA   | LE TOP-COATS   |   |                                |                        |                               |  |
| Recommended Uses<br>Suitable Top-Coats   | First coat for steel structures, metal surfaces and maintenance operations.<br>Alkyd paints, chlorinated rubber coatings and synthetic enamels.                              |   |                                |                        |                               |  |
| CHEMICAL COMPOS  | SITION   |   |                                |                        |                               |  |
| Type of Binder   | Specially Selected Alkyd Resin   |   | Red Lead Content in Dried Film |                        | 60 ± 1% By Weight             |  |
| Number of Component(s)   | 1 Component  |   | Solid Content                  |                        | 80 ± 1% By Weight             |  |
| Curing Mechanism   | Solvent Evaporation and Oxidation  |   |                                |                        | 63 ± 2% By Volume             |  |
| Main Pigment(s)  | Red- Lead Oxide  |   |                                | Flash Point            | 28°C (82°F)                   |  |
| PHYSICAL PROPER  | TIES   |   |                                |                        |                               |  |
| Finish   | Semi flat  |   |                                |                        |                               |  |
| Colour   | Deep Orange (RAL-2011)   |   |                                |                        |                               |  |
| Specific Gravity   | 1.55 ± 0.05 gr/cm <sup>3</sup>   | -   |                                |                        |                               |  |
| Heat Resistance Continuous Service: 90°C   |  |   |                                |                        |                               |  |
|  | Non-Continuous Service   | :: 120°C  |                                |                        |                               |  |
| APPLICATION DETA   | ILS  |   |                                |                        |                               |  |
| Surface Preparation  | All oil, grease, dirt and other contaminants must be removed from the surface. Wire Brush or sandblast according to Swedish Standard (SIS 5900)St. 2 or Sa 2 is recommended. |   |                                |                        |                               |  |
| Theoretical Consumption  | 120 gr/m² @ 50 Microns DFT   |   |                                |                        |                               |  |
| Paint Application  | Methods  | Airless Spray   | Air Spray                      | Brush                  | Roller                        |  |
|  | Nozzle Size  | 0.011" - 0.015"   | 1.80 mm                        |                        |                               |  |
|  | Pump Ratio<br>Air Pressure   | 1 / 45<br>4 – 6 Bar   | <br>3 – 5 Bar                  |                        |                               |  |
|  | Thinning   | 5 – 10% T-411   | 10 – 15% T-411                 | 3 – 5% T-411           | 3 – 5% T-411                  |  |
| Film Thickness   |  | Recommende  |                                | nimum                  | Maximum                       |  |
|  | Wet Film Thickness (µm<br>Dry Film Thickness (µm)  | ,   |                                | 65<br>40               | <u>160</u><br>100             |  |
| Drying Time  | Dust Free Time   | Tack Free Time  | Dry to Handle                  | Fully Cured            | Recoating Interval            |  |
|  | 30 – 40 Minutes  | 4 – 6 Hours   | 12 – 16 Hours                  | 10-20 Days             | Min. 24 Hours<br>Max. 14 Days |  |
| *Drying time calculated at 25°C according to ASTM test method D-1640 for 100 $\mu$ m WFT |  |   |                                |                        |                               |  |
| Application Limits   | Relative Humidity  | Min   |                                | Max. 80%<br>Max. +40°C |                               |  |
|  | Temperature<br>Substrate Temperature*  |   |                                |                        |                               |  |
|  | · · · · · · · · · · · · · · · · · · ·  | Substrate Temperature* Min. +5°C Max. +45°C   *Please note that the substrate temperature should be at least 5°C above the dew point  |                                |                        |                               |  |
| Recommendations  |  | -Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.<br>-Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-411. |                                |                        |                               |  |
| PACKING, STORAGE   | E AND SAFETY   |   |                                |                        |                               |  |
| Packing  | 4 Litres (5 kgs. Net) and  | 4 Litres (5 kgs. Net) and 20 Litres (25 kgs. Net) Containers.   |                                |                        |                               |  |
| Storage Conditions   | To be stored in cool and   | To be stored in cool and dry conditions in original sealed containers.  |                                |                        |                               |  |
| Shelf Life   | At least 12 months after d   | At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.   |                                |                        |                               |  |
| Safety   | This product contains or   | This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and   |                                |                        |                               |  |
| -  |  | hine and out of children's  |                                |                        |                               |  |
|  | •••  |   |                                | na application. Use v  | with adequate ventilation.    |  |
|  | · • ·  |   |                                | 0                      |                               |  |

www.ronass.com

9

ACA CE

Pias I