

A single-pack, high-gloss baking finish coat with excellent adhesion, outdoor stability, mechanical resistances and anti-corrosive properties.

USES AND SUITABLE PRIMERS

Recommended Uses	Top-coat or single coating system for industrial products such as electrical and electronic equipment cases, steel furniture and metallic finished goods.
Suitable Primers	RTB-1204 (Semi-Flat Baking Enamel)

CHEMICAL COMPOSITION

Type of Binder	Melamine – Alkyd Resins.	Solid Content	64 ± 2% By Weight
Number of Component(s)	1 Component		47 ± 2% By Volume
Curing Mechanism	Thermosetting	Flash Point	29°C (84°F)

PHYSICAL PROPERTIES

Finish	Gloss
Colour	Wide range available according to RAL and BS colour systems
Specific Gravity	1.25 ± 0.05 gr/cm ³

APPLICATION DETAILS

Surface Preparation	All oil, grease, dirt and other contaminants must be removed from the surface. Degreasing and chemical preparation or wire brush and treatment with a suitable primer is recommended.
---------------------	---

Theoretical Consumption	110 gr/m ² @ 40 Microns DFT
-------------------------	--

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.009" – 0.013"	1.60 or 1.80 mm	---	---
	Pump Ratio	1 / 28	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	5 – 10% T-1206	10 – 20% T-1206	3 – 5% T-1206	3 – 5% T-1206

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	85	50	105
	Dry Film Thickness (µm)	40	25	50

Baking Conditions	Flash-Off Time	5 – 10 Minutes at Room Temperature
	Stoving Time	30 Minutes at 120°C or 20 Minutes at 150°C

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

*Please note that the substrate temperature should be at least 5°C above the dew point

Recommendations	Clean tools thoroughly before and immediately after use with cleaning solvent T-111, T-726 or T-1206.
-----------------	---

PACKING, STORAGE AND SAFETY

Packing	20 Litres Containers (25 kgs. Net)
Storage Conditions	To be stored in cool and dry conditions in original sealed containers. Keep away from direct sunshine.
Shelf Life	At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.
Safety	This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach. Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.