

Special heavy-duty two-component epoxy coating specifically formulated for splash zone areas and underwater application, featuring excellent mechanical properties and outstanding filling and adhesion capabilities for both dry and wet surfaces.

USES

Recommended Uses Single coating system recommended for a wide range of applications including the protection of risers, piles, water pipes and structures below the splash zone, and in off-shore areas. This product is also used to repair holes, leaks, cracks and other defects with minimum effort and downtime.
Specifically designed for application underwater or in very wet areas as a protective coating for poorly prepared metal and concrete substrates. Ideal for use on wet and saturated metal and concrete, and for hand-prepared or hydro-blasted surfaces.

CHEMICAL COMPOSITION

Type of Binder	Epoxy Vinyl – Polyamide	Solid Content After Mixing	100% By Weight
Number of Component(s)	2 Components		100% By Volume
Curing Mechanism	Chemical Reaction	Flash Point	150°C (300°F)

PHYSICAL PROPERTIES

Finish	Semi gloss
Colour	Wide range available according to RAL colour system
Specific Gravity after Mixing	1.50 ± 0.05 gr/cm ³

APPLICATION DETAILS

Surface Preparation	<u>Above Water:</u> Remove all loose contamination by wire brushing or scraping. For small areas, roughen with a mechanical abradar. For larger areas, a suitable angular metallic or non-metallic abrasive should be chosen to give a minimum profile of 120 µm. Abrasive blast the surface to Swedish Standard (SIS 5900) Sa 2½. (Roughness: min 120 µm). <u>Underwater:</u> Remove all loose contamination by wire brushing or scraping. Remove any scale, dirt and grease with waterproof abrasive paper.				
Mixing Ratio	Component A: 100 Parts by weight Component B: 40 Parts by weight				
Mixing Instructions	Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 5 minutes. Keep the mixture for 5 additional minutes prior to thinning down to allow for the pre-reaction time.				
Pot Life	3.5 Hours at 5°C 3 Hours at 10°C 2.5 Hours at 15°C 2 Hours at 20°C				
Theoretical Consumption	1500 gr/m² @ 1000 Microns DFT				
Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.031" – 0.049"	---	---	---
	Pump Ratio	1 / 68	---	---	---
	Air Pressure	5 – 8 Bar	---	---	---
	Thinning	Never thin down product			
Method of Application	Above Water	Airless Spray, Brush, Roller, Trowel			
	Underwater	Syringe, Trowel, Spreading Knife, Spatula, Mitts			
Film Thickness	Wet Film Thickness (µm)	Up to 2000 Microns			
	Dry Film Thickness (µm)	Up to 2000 Microns			
Drying Time		5°C	10°C	15°C	20°C
	Curing Time	12 Hours	10 Hours	8 Hours	6 Hours
	Complete Curing Time	1 Day	11 Days	9 Days	7 Days
	Recoating Time	Unlimited			
Application Limits	Relative Humidity	Min. ---		Max. ---	
	Temperature	Min. +5°C		Max. +40°C	
Recommendations	Clean tools thoroughly before and immediately after use with T-445.				

PACKING, STORAGE AND SAFETY

Packing Component A(Epoxy): 20 Litres Containers (5 kgs. Net) and Component B(Hardener): 10 Litres Containers (2.5 kgs. Net)

Storage Conditions To be stored in cool and dry conditions in original sealed containers.

Shelf Life At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.

Safety This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach.
Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.