

Special high-build, two-component Zinc-Rich Epoxy Coating reinforced with Micaceous Iron Oxide with excellent adhesion, durability, and anti-corrosive properties.

### USES AND SUITABLE TOP-COATS

|                    |  |
|--------------------|--|
| Recommended Uses   | First coat and single coating system for steel structures, maintenance operations, and brushed and sandblasted metal surfaces. |
| Suitable Top-Coats | RTB-1312 can be over-coated with a wide range of epoxy coatings and polyurethane systems.                                      |

### CHEMICAL COMPOSITION

|                        |   |                            |                   |
|------------------------|---|----------------------------|-------------------|
| Type of Binder         | Epoxy – Polyamide                             | Zinc Content in Dried Film | 61 ± 1% By Weight |
| Number of Component(s) | 2 Components                                  | Solid Content After Mixing | 85 ± 1% By Weight |
| Curing Mechanism       | Chemical Reaction                             |                            | 62 ± 2% By Volume |
| Main Pigment(s)        | Metallic Zinc Powder and Micaceous Iron Oxide | Flash Point                | 28°C (82°F)       |

### PHYSICAL PROPERTIES

|                               |                                |
|-------------------------------|--------------------------------|
| Finish                        | Flat                           |
| Colour                        | Dark Grey                      |
| Specific Gravity after Mixing | 2.15 ± 0.05 gr/cm <sup>3</sup> |
| Thermal Tolerance             | Min -60°C      Max 145°C       |

### APPLICATION DETAILS

|                     |  |
|---------------------|--|
| Surface Preparation | All oil, grease, dirt and other contaminants must be removed from the surface. Sandblast according to Swedish Standard (SIS 5900). Sa 2 ½ or Sa 3 or Nace#2 is recommended.  |
| Mixing Ratio        | Component A: 100 Parts by weight      Component B: RTB-1312-B or RTB-9000 10 Parts by weight   |
| Mixing Instructions | Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 5 minutes. Keep the mixture for 5 additional minutes prior to thinning down to allow for the pre-reaction time. Do not thin down each component separately. |

|                         |  |
|-------------------------|--|
| Pot Life                | 4 Hours at 25°C                        |
| Theoretical Consumption | 280 gr/m <sup>2</sup> @ 80 Microns DFT |

|                   |              |                 |               |              |              |
|-------------------|--------------|-----------------|---------------|--------------|--------------|
| Paint Application | Methods      | Airless Spray   | Air Spray     | Brush        | Roller       |
|                   | Nozzle Size  | 0.013" – 0.017" | 1.80 mm       | ---          | ---          |
|                   | Pump Ratio   | 1 / 45          | ---           | ---          | ---          |
|                   | Air Pressure | 3 – 5 Bar       | 3 – 5 Bar     | ---          | ---          |
|                   | Thinning     | 3 – 7% T-445    | 6 – 12% T-445 | 2 – 4% T-445 | 2 – 4% T-445 |

|                |                         |             |         |         |
|----------------|-------------------------|-------------|---------|---------|
| Film Thickness |                         | Recommended | Minimum | Maximum |
|                | Wet Film Thickness (µm) | 160         | 130     | 235     |
|                | Dry Film Thickness (µm) | 100         | 80      | 145     |

|             |                 |                 |               |             |                              |
|-------------|-----------------|-----------------|---------------|-------------|------------------------------|
| Drying Time | Dust Free Time  | Tack Free Time  | Dry to Handle | Fully Cured | Recoating Interval           |
|             | 10 – 20 Minutes | 30 – 60 Minutes | 3 – 4 Hours   | 10-14 Days  | Min. 8 Hours<br>Max. 10 Days |

*\*Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

|                    |                        |           |            |
|--------------------|------------------------|-----------|------------|
| Application Limits | Relative Humidity      | Min. ---  | Max. 80%   |
|                    | Temperature            | Min. +5°C | Max. +40°C |
|                    | Substrate Temperature* | Min. +5°C | Max. +45°C |

*\*Please note that the substrate temperature should be at least 5°C above the dew point*

|                 |   |
|-----------------|---|
| Recommendations | -Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.<br>-Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-445. |
|-----------------|---|

### PACKING, STORAGE AND SAFETY

|                    |   |
|--------------------|---|
| Packing            | Component A (Epoxy): 10 Litres Containers (18 kgs. Net) and Component B (Hardener): 4 Litres Containers (1.8 kgs. Net)  |
| Storage Conditions | To be stored in cool and dry conditions in original sealed containers.  |
| Shelf Life         | 9 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.   |
| Safety             | This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach.<br>Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation. |