



RONAGUARD 1412

RTB-1412 (Two-Component Epoxy Primer)

Two-component modified high-build epoxy primer with excellent anti-corrosive, adhesion, and chemical properties, as well as excellent heat resistances on atmospheric and immersion services.

USES AND SUITABLE TOP-COATS

Recommended Uses	Primer and single coating system for steel structures, maintenance operations, and brushed and sandblasted metal surfaces in marine and offshore environments.
Suitable Top-Coats	Ronaguard-1412 coatings can be over-coated with a wide range of epoxy coatings and polyurethane systems. This coating can also be applied as a single coating system.

CHEMICAL COMPOSITION

Type of Binder	Epoxy –Polyamino-Amide	Solid Content After Mixing	78± 1% By Weight
Number of Component(s)	2 Components		60 ± 2% By Volume
Curing Mechanism	Chemical Reaction	Flash Point	29°C (84°F)

PHYSICAL PROPERTIES

Finish	Flat
Colour	Window Grey (RAL-7040).
Specific Gravity after Mixing	1.55 ± 0.05 gr/cm ³

APPLICATION DETAILS

Surface Preparation All oil, grease, dirt and other contaminants must be removed from the surface. Sandblast according to Swedish Standard (SIS 5900). Sa 2 ½, and treatment with an epoxy primer is recommended.

Mixing Ratio Component A: 100 Parts by weight Component B :RTB-9400 10 Parts by weight
Component A: 6 Parts by volume Component B :RTB-9400 1 Parts by volume

Mixing Instructions Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 10 minutes. Keep the mixture for 5 additional minutes prior to thinning down to allow for the pre-reaction time. Do not thin down each component separately.

Pot Life 4 Hours at 25°C

Theoretical Consumption 260 gr/m² @ 100 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.017" – 0.023"	1.80 mm	---	---
	Pump Ratio	1/45	---	---	---
	Air Pressure	4 – 6 Bar	3 – 5 Bar	---	---
	Thinning	8 – 15% T-445	10 – 20% T-445	3 – 5% T-445	2 – 4% T-445

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	250	125	350
	Dry Film Thickness (µm)	150	75	210

Drying Time	Substrate Temp.	10°C	25°C	35°C
	Tack Free Time	5-6 Hours	3-4 Hours	2-3 Hours
	Dry to Handle	24-30 Hours	8-12Hours	12-18 Hours
	Recoating Time	Min. 8 Hours	Min. 8 Hours	Min. 8 Hours
		Max. 11 Days	Max. 10 Days	Max. 9 Days

**Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

**Please note that the substrate temperature should be at least 5°C above the dew point*

Recommendations -Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.
-Clean tools thoroughly before and immediately after use with cleaning solvent T-440 or T-445.

PACKING, STORAGE AND SAFETY

Packing	Component A (Epoxy): 20 Liter Containers Component B (Hardener): 5 Liter Containers
Storage Conditions	To be stored in cool and dry conditions in original sealed containers.
Shelf Life	At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.
Safety	This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach. Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.