

| Special one-component synthetic primer with excellent adhesion, hiding power and anti-corrosive properties.   |  |                              |           |                          |                  |                                     |
|---|--|------------------------------|-----------|--------------------------|------------------|-------------------------------------|
| USES AND SUITABALE TOP-COATS  |  |                              |           |                          |                  |                                     |
| Recommended Uses  | First coat or single coating system for brushed and sandblasted steel surfaces and maintenance operations in<br>atmospheric service up to 80°C.                      |                              |           |                          |                  |                                     |
| Suitable Top-Coats  | Depending on service conditions, RTB-304 can be over-coated by a wide range of alkyd paints, chlorinated rubber coatings or vinyl systems.                           |                              |           |                          |                  |                                     |
| CHEMICAL COMPOSITION  |  |                              |           |                          |                  |                                     |
| Type of Binder  | Modified Alkyd Resin   |                              |           |                          | Solid Content    | 70 ± 1% By Weight                   |
| Number of Component(s)  | 1 Component  |                              |           |                          |                  | 54 ± 2% By Volume                   |
| Curing Mechanism  | Solvent Evaporation and Oxidation  |                              |           |                          | Flash Point      | 28°C (82°F)                         |
| Main Pigment(s)   | Red and Black Iron Oxide   |                              |           |                          |                  |                                     |
| PHYSICAL PROPERTIES   |  |                              |           |                          |                  |                                     |
| Finish  | Semi flat  |                              |           |                          |                  |                                     |
| Colour  | Dark Brown (Comparable with RAL-8016: Mahogany Brown)  |                              |           |                          |                  |                                     |
| Specific Gravity  | $1.30 \pm 0.05 \text{ gr/cm}^3$  |                              |           |                          |                  |                                     |
| APPLICATION DETAILS   |  |                              |           |                          |                  |                                     |
| Surface Preparation   | All oil, grease, dirt and other contaminants must be removed from the surface. Wire Brush or sandblast according to Swedish Standard (SIS 5900)St. 2 is recommended. |                              |           |                          |                  |                                     |
| Theoretical Consumption   | 120 gr/m² @ 50 Microns DFT   |                              |           |                          |                  |                                     |
| Paint Application   | Methods  | Airless Spray                | Air Spray |                          | Brush            | Roller                              |
|   | Nozzle Size  | 0.011" – 0.013"              | 1.80 mm   |                          |                  |                                     |
|   | Pump Ratio   | 1/28                         |           |                          |                  |                                     |
|   | Air Pressure<br>Thinning   | 3 – 4.5 Bar<br>5 – 10% T-411 |           | 3 – 5 Bar<br>- 20% T-411 | <br>3 – 5% T-411 | <br>2 – 4% T-411                    |
|   | типпу  |                              |           | -                        |                  |                                     |
| Film Thickness  |  | Recommended                  |           |                          |                  | Maximum                             |
|   | Wet Film Thickness (µm)<br>Dry Film Thickness (µm)   | 95<br>50                     |           | 7                        |                  | <u>110</u><br>60                    |
| Daving Time   | , , ,  |                              |           |                          |                  |                                     |
| Drying Time   | Dust Free Time   | 3 – 4 Hours 12 –             |           | Dry to I                 |                  | Recoating Interval<br>Min. 24 Hours |
|   | 20 – 40 Minutes  |                              |           | 12 – 16 Hours            |                  | Max. 14 Days                        |
|   | *Drying time calculated at 2   | 5°C according to AST         | M test r  | nethod D-1640 f          | for 100 µm WFT   |                                     |
| Application Limits  | Relative Humidity Min  |                              | Max. 80%  |                          |                  |                                     |
|   | Temperature  | Min. +5°C                    |           |                          | Max. +40°C       |                                     |
|   | Substrate Temperature*<br>*Please note that the substr   | Min. +5°C                    | d ha at   | loast 5°C abov           | Max. +45°C       |                                     |
| Decommondations   |  |                              |           |                          |                  | Instruction Looflat                 |
| Recommendations -Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.<br>-Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-411. |  |                              |           |                          |                  |                                     |
| PACKING, STORAGE AND SAFETY   |  |                              |           |                          |                  |                                     |
| Packing   | 10 Litres (10 kgs. Net) and 20 Litres (25 kgs. Net) Containers.  |                              |           |                          |                  |                                     |
| Storage Conditions  | To be stored in cool and dry conditions in original sealed containers.   |                              |           |                          |                  |                                     |
| Shelf Life  | At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.  |                              |           |                          |                  |                                     |
| Safety  | This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and  |                              |           |                          |                  |                                     |
|   | aguinmente direct sunshine and out of children's reach   |                              |           |                          |                  |                                     |

equipments, direct sunshine and out of children's reach.

w

Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.

U

onass, com

**REVISION:2024**