

High-gloss synthetic enamel with excellent hiding power, excellent weather resistance, very good outdoor stability and gloss retention.

### USES AND SUITABLE PRIMERS

Recommended Uses	Top-coat for metal surfaces and maintenance operations.
Suitable Primers	Alkyd and other synthetic primers.

### CHEMICAL COMPOSITION

Type of Binder	Modified Alkyd Resin	Solid Content	55 ± 3% By Weight
Number of Component(s)	1 Component		44 ± 2% By Volume
Curing Mechanism	Solvent Evaporation and Oxidation		
Main Pigment(s)	Non-Toxic Inert Pigments	Flash Point	28°C (82°F)

### PHYSICAL PROPERTIES

Finish	Gloss
Colour	Wide range available according to RAL and BS colour systems
Specific Gravity	1.05 ± 0.15 gr/cm <sup>3</sup>
Heat Resistance	Continuous Service: 80°C Non-Continuous Service: 120°C

### APPLICATION DETAILS

Surface Preparation	All oil, grease, dirt and other contaminants must be removed from the surface. Wire brush or sandblast according to the surface condition, and treatment with a suitable primer is recommended.
---------------------	---

Theoretical Consumption	100 gr/m <sup>2</sup> @ 40 Microns DFT
-------------------------	--

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.009" – 0.013"	1.60 or 1.80 mm	---	---
	Pump Ratio	1/ 28	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	5 – 10% T-411	15 – 20% T-411	3 – 5% T-411	3 – 5% T-411

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	105	60	150
	Dry Film Thickness (µm)	45	25	65

Drying Time	Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
	30 – 60 Minutes	2 – 3 Hours	4 – 6 Hours	7-10 Days	Min. 24 Hours Max. 14 Days

\*Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

\*Please note that the substrate temperature should be at least 5°C above the dew point

Recommendations	-Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet. -Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-411.
-----------------	---

### PACKING, STORAGE AND SAFETY

Packing	20 Litres Containers (25 kgs. Net)
Storage Conditions	To be stored in cool and dry conditions in original sealed containers.
Shelf Life	At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.
Safety	This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach.  Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.