

A single-pack, high performance water-based acrylic coating with excellent adhesion. This coating also has exceptional chemical, moisture, weather and ultra-violet resistances in atmospheric service.

USES AND SUITABLE PRIMERS

Recommended Uses	This coating can be used as a protective and decorative coating for concrete surfaces and other masonry substrates, especially in aggressive, polluted and coastal environments.
Suitable Primers	RTB-750 (Two-Component Epoxy Sealer) and RTB-788 (Epoxy Pink Putty).

CHEMICAL COMPOSITION

Type of Binder	Water-Reducible Acrylic Resin	Solid Content	64 ± 1% By Weight
Number of Component(s)	1 Component		40 ± 2% By Volume
Curing Mechanism	Solvent Evaporation	Flash Point	---

PHYSICAL PROPERTIES

Finish	Flat
Colour	Wide range available according to RAL colour system.
Specific Gravity	1.40 ± 0.05 gr/cm ³

APPLICATION DETAILS

Surface Preparation All oil, grease, dirt and other contaminants must be removed, and the surface must be fully dried. Priming with a suitable sealer or RTB-788 (Ronass Epoxy Pink Putty) is recommended.

Theoretical Consumption 280 gr/m² @ 80 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.015" – 0.017"	1.80 mm	---	---
	Pump Ratio	1 / 45	---	---	---
	Air Pressure	3 – 4.5 Bar	3 – 5 Bar	---	---
	Thinning	20 – 25% Water	40 – 50% Water	40 – 50% Water	40 – 50% Water

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	200	150	250
	Dry Film Thickness (µm)	80	60	100

Drying Time	Dust Free Time	Tack Free Time	Recoating Interval
	30 Minutes	1 Hour	Min. 8 Hours

*Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +35°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

*Please note that the substrate temperature should be at least 5°C above the dew point

*Please note that the relative substrate humidity should be lower than 5%

Recommendations Clean tools thoroughly before and immediately after use with plenty of water.

PACKING, STORAGE AND SAFETY

Packing	20 Litres Containers (10 kgs Net)
Storage Conditions	To be stored in cool and dry conditions within a temperature range of +5°C minimum and +40°C maximum in original sealed containers. Keep away from freezing temperatures.
Shelf Life	At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.
Safety	Personal protective equipment is recommended when applying paint. Avoid painting in the open area while it is raining or stormy. If some paint remains in the can. Close it tightly to prevent drying and keep it safely for next use..