

Special one-component phenolic primer and intermediate coating with excellent adhesion and anti-corrosive properties.

USES AND SUITABLE TOP-COATS

Recommended Uses	First coat for steel structures, metal surfaces and maintenance operations.
Suitable Top-Coats	Alkyd paints, chlorinated rubber coatings and synthetic enamels.

CHEMICAL COMPOSITION

Type of Binder	Modified Phenolic Resin	Solid Content	70 ± 1% By Weight
Number of Component(s)	1 Component		57 ± 2% By Volume
Curing Mechanism	Chemical Reaction	Flash Point	28°C (82°F)

PHYSICAL PROPERTIES

Finish	Semi flat
Colour	Oxide Red (RAL-3009)
Specific Gravity	1.20 ± 0.05 gr/cm ³

APPLICATION DETAILS

Surface Preparation All oil, grease, dirt and other contaminants must be removed from the surface. Sandblast according to the surface conditions is recommended.

Theoretical Consumption 105 gr/m² @ 50 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.011" – 0.015"	1.80 mm	---	---
	Pump Ratio	1 / 28	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	5 – 10% T-265	10 – 20% T-265	2 – 5% T-265	2 – 5% T-265

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	90	70	105
	Dry Film Thickness (µm)	50	40	60

Drying Time	Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
	20 – 40 Minutes	1 – 2 Hours	16 – 24 Hours	7 Days	Min. 16 Hours Max. 14 Days

*Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

*Please note that the substrate temperature should be at least 5°C above the dew point

Recommendations -Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.
-Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-265.

PACKING, STORAGE AND SAFETY

Packing 20 Litres Containers (25 kgs. Net)

Storage Conditions To be stored in cool and dry conditions in original sealed containers.

Shelf Life At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.

Safety This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach.

Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.