

Two-component epoxy coating with excellent adhesion and anti-corrosive properties as well as great chemical and water resistances.

### USES AND SUITABLE TOP-COATS

Recommended Uses	Primer, intermediate or single coating system for maintenance works, protective coating system and interior coatings for vessels, water tanks and pipelines.
Suitable Top-Coats	RTB-716-R can be over-coated by itself or RTB-727-R (Two-Component Epoxy Coating).

### CHEMICAL COMPOSITION

Type of Binder	Epoxy – Polyaminoamide	Solid Content After Mixing	80 ± 1% By Weight
Number of Component(s)	2 Components		60 ± 2% By Volume
Curing Mechanism	Chemical Reaction	Flash Point	28°C (82°F)

### PHYSICAL PROPERTIES

Finish	Semi gloss
Colour	Dark Brown (Component A: Black   Component B: Red)
Specific Gravity after Mixing	1.70 ± 0.10 gr/cm <sup>3</sup>

### APPLICATION DETAILS

Surface Preparation	All oil, grease, dirt and other contaminants must be removed from the surface. Sandblast according to Swedish Standard (SIS 5900) Sa. 3 and treatment with RTB-496 (H.C Zinc-Rich Epoxy Primer) is recommended.
Mixing Ratio	Component A: 100 Parts by weight    Component B: 15 Parts by weight    RTB-716-R-B
Mixing Instructions	Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 5 minutes. Keep the mixture for 5 additional minutes prior to thinning down to allow for pre-reaction time. Do not thin down each component separately.
Pot Life	2 Hours at 25°C
Theoretical Consumption	285 gr/m <sup>2</sup> @ 100 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.013" – 0.017"	1.80 mm	---	---
	Pump Ratio	1 / 45	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	5 – 10% T-445	8 – 15% T-445	3 – 5% T-445	2 – 4% T-445

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	150	100	185
	Dry Film Thickness (µm)	90	60	110

Drying Time	Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
	1 – 2 Hours	3 – 4 Hours	10 – 12 Hours	7 – 10 Days	Min. 8 Hours Max. 10 Days

*\*Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

*\*Please note that the substrate temperature should be at least 5°C above the dew point*

Recommendations	-Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet. -Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-445.
-----------------	---

### PACKING, STORAGE AND SAFETY

Packing	Component A(Epoxy): 20 Litres Containers (25 kgs. Net) and Component B(Hardener): 6 Litres Containers (3.75 kgs. Net)
Storage Conditions	To be stored in cool and dry conditions in original sealed containers.
Shelf Life	At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.
Safety	This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach.  Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.