

Two-component epoxy coating with excellent adhesion and anti-corrosive properties, as well as great chemical and water resistances.

USES AND SUITABLE PRIMERS

Recommended Uses	Primer, intermediate and finish coat for maintenance works, protective coating systems and interior coatings for vessels and water tanks and pipeline.
Suitable Primers	RTB-496 (Zinc-Rich Epoxy Primer), RTB-1180 (Special Zinc-Rich Epoxy Primer), RTB-1185 (Zinc-Rich Epoxy Primer), RTB-716-R (Two-Component Epoxy Coating) and RTB-867 (Zinc Phosphate/ Iron Oxide Epoxy Primer).

CHEMICAL COMPOSITION

Type of Binder	Epoxy – Polyaminoamide	Solid Content After Mixing	80 ± 1% By Weight
Number of Component(s)	2 Components		62 ± 2% By Volume
Curing Mechanism	Chemical Reaction		
Main Pigment(s)	Inorganic Inert Pigments	Flash Point	28°C (82°F)

PHYSICAL PROPERTIES

Finish	Gloss
Colour	Pure White (RAL-9010)- Light Grey(RAL-7035)
Specific Gravity after Mixing	1.60 ± 0.05 gr/cm ³

APPLICATION DETAILS

Surface Preparation	All oil, grease, dirt and other contaminants must be removed from the surface. Sandblast according to Swedish Standard(SIS 5900) Sa 3 and treatment with RTB-496 (H.C Zinc-Rich Epoxy Primer) and RTB-716-R (Two-Component Epoxy Coating) is recommended.
---------------------	---

Mixing Ratio	Component A: 100 Parts by weight Component B: RTB-727-R-B or RTB-9500 10 Parts by weight
--------------	---

Mixing Instructions	Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 5 minutes. Keep the mixture for 5 additional minutes prior to thinning down to allow for pre-reaction time. Do not thin down each component separately.
---------------------	--

Pot Life	2 Hours at 25°C
----------	-----------------

Theoretical Consumption	310 gr/m ² @ 120 Microns DFT
-------------------------	---

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.013" – 0.017"	1.80 mm	---	---
	Pump Ratio	1 / 45	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	5 – 15% T-445	10 – 20% T-445	2 – 4% T-445	2 – 4% T-445

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	190	160	320
	Dry Film Thickness (µm)	120	100	200

Drying Time	Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
	45 – 60 Minutes	2 – 3 Hours	6 – 8 Hours	7 – 10 Days	Min. 16 Hours Max. 10 Days

**Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

**Please note that the substrate temperature should be at least 5°C above the dew point*

Recommendations	-Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet. -Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-445.
-----------------	---

PACKING, STORAGE AND SAFETY

Packing	Component A(Epoxy): 20 Litres Containers (25 kgs. Net) and Component B(Hardener): 4 Litres Containers (2.5 kgs. Net)
Storage Conditions	To be stored in cool and dry conditions in original sealed containers.
Shelf Life	At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.
Safety	This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach. Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.