

An aliphatic polyurethane coating with excellent outdoor stability, durability, and remarkable mechanical, chemical, weather and excellent ultra-violet radiation resistances.

USES AND SUITABLE PRIMERS

Recommended Uses Finish coat for protective coating systems, maintenance operations and primed metal surfaces.
Suitable Primers Epoxy primers and intermediate epoxy coatings.

CHEMICAL COMPOSITION

Type of Binder	Polyester – Isocyanate	Solid Content After Mixing	67 ± 3% By Weight
Number of Component(s)	2 Components		51 ± 3% By Volume
Curing Mechanism	Chemical Reaction	Flash Point	28°C (82°F)

PHYSICAL PROPERTIES

Finish Gloss
Colour Wide range available according to RAL and BS colour systems
Specific Gravity after Mixing 1.25 ± 0.05 gr/cm³

APPLICATION DETAILS

Surface Preparation All oil, grease, dirt and other contaminants must be removed from the surface. Sandblast according to Swedish Standard(SIS 5900). Sa. 2 ½ and treatment with an epoxy primer and intermediate coating is recommended.

Mixing Ratio Component A: (Base) 100 Parts by weight Component B: (Hardener) RTB-828-B or RTB-9200 20 Parts by weight

Mixing Instructions Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 5 minutes. Do not thin down each component separately.

Pot Life 4 Hours at 25°C

Theoretical Consumption 125 gr/m² @ 50 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.009" – 0.013"	1.80 mm	---	---
	Pump Ratio	1 / 28	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	5 – 10% T-849	15 – 25% T-849	3 – 5% T-849	---

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	120	80	140
	Dry Film Thickness (µm)	60	40	70

Drying Time	Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
	1 – 2 Hours	6 – 8 Hours	12 – 16 Hours	5-7 Days	Not Applicable

**Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

**Please note that the substrate temperature should be at least 5°C above the dew point*

Recommendations -Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.
 -Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-849.

PACKING, STORAGE AND SAFETY

Packing Component A(Base): 20 Litres Containers (25 kgs. Net) and Component B(Hardener): 6 Litres Containers (5 kgs. Net)

Storage Conditions To be stored in cool and dry conditions in original sealed containers.

Shelf Life At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.

Safety This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments,direct sunshine and out of children's reach.
 Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.