

A high-build synthetic primer based on Micaceous Iron Oxide with excellent adhesion, corrosion protection, and durability.

USES AND SUITABLE TOP-COATS

Recommended Uses	first coat for steel structures and metal surfaces.
Suitable Top-Coats	Alkyd paints, chlorinated rubber coatings and synthetic enamels.

CHEMICAL COMPOSITION

Type of Binder	Specially Selected Alkyd Resin	Solid Content	75 ± 1% By Weight
Number of Component(s)	1 Component		60 ± 2% By Volume
Curing Mechanism	Solvent Evaporation and Oxidation		
Main Pigment(s)	Micaceous Iron Oxide	Flash Point	28°C (82°F)

PHYSICAL PROPERTIES

Finish	Flat
Colour	Mahogany Brown (RAL-8016) and Basalt Grey (RAL-7012)
Specific Gravity	1.40 ± 0.05 gr/cm ³

APPLICATION DETAILS

Surface Preparation All oil, grease, dirt and other contaminants must be removed from the surface. Wire brush or sandblast according to Swedish Standard(SIS 5900). Sa 2 is recommended.

Theoretical Consumption 185 gr/m² @ 80 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.013" – 0.017"	1.80 mm	---	---
	Pump Ratio	1 / 28	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	5 – 10% T-822	10 – 20% T-822	3 – 5% T-822	3 – 5% T-822

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	135	100	165
	Dry Film Thickness (µm)	80	60	100

Drying Time	Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
	20 – 40 Minutes	1 – 2 Hours	8 – 12 Hours	10-20 Days	Min. 24 Hours Max. 14 Days

**Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

**Please note that the substrate temperature should be at least 5°C above the dew point*

Recommendations

- Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.
- Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-822.

PACKING, STORAGE AND SAFETY

Packing	6 10 L 20 L
Storage Conditions	To be stored in cool and dry conditions in original sealed containers.
Shelf Life	At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.
Safety	This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach. Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.