



# RONASS ZINC PHOSPHATE/ IRON OXIDE EPOXY PRIMER RTB-867 (A&B COMPONENTS)

Special two-component primer with excellent adhesion and anti-corrosive properties.

## USES AND SUITABLE TOP-COATS

Recommended Uses	First coat for steel structures and metal surfaces, or as a single coating system in maintenance operations. This coating can be used as the first coat of interior coating systems for potable water tanks and pipelines.
Suitable Top-Coats	Alkyd paints, chlorinated rubber coatings, epoxy coatings and polyurethane systems.

## CHEMICAL COMPOSITION

Type of Binder	Epoxy – Polyamide	Solid Content After Mixing	75 ± 1% By Weight
Number of Component(s)	2 Components		54 ± 2% By Volume
Curing Mechanism	Chemical Reaction		
Main Pigment(s)	Zinc Phosphate and other Active Pigments.	Flash Point	29°C (84°F)

## PHYSICAL PROPERTIES

Finish	Semi flat
Colour	Grey (RAL-7000), Sand Yellow (RAL-1002), Oxide Red (RAL-3009) .
Specific Gravity after Mixing	1.55 ± 0.07 gr/cm <sup>3</sup>

## APPLICATION DETAILS

Surface Preparation	All oil, grease, dirt and other contaminants must be removed from the surface. Sandblast according to the Swedish Standard(SIS 5900). Sa 2 ½ or greater is recommended.
Mixing Ratio	Component A: 100 Parts by weight      Component B: RTB-867-B or RTB-9600 15 Parts by weight
Mixing Instructions	Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 5 minutes. Keep the mixture for 5 additional minutes prior to thinning down to allow for the pre-reaction time. Do not thin down each component separately.
Pot Life	4 Hours at 25°C
Theoretical Consumption	145 gr/m <sup>2</sup> @ 50 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.011" – 0.015"	1.80 mm	---	---
	Pump Ratio	1 / 45	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	7 – 10% T-445	15 – 20% T-445	3 – 5% T-445	3 – 5% T-445

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	110	45	185
	Dry Film Thickness (µm)	60	25	100

Drying Time	Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
	20 – 40 Minutes	1 – 2 Hours	4 – 6 Hours	10-14 Days	Min. 8 Hours Max. 10 Days

*\*Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

*\*Please note that the substrate temperature should be at least 5°C above the dew point*

Recommendations	-Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet. -Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-445.
-----------------	---

## PACKING, STORAGE AND SAFETY

Packing	Component A (Epoxy): 20 Litres Containers (25 kgs. Net) and Component B(Hardener): 4 Litres Containers (3.75 kgs. Net)
Storage Conditions	To be stored in cool and dry conditions in original sealed containers.
Shelf Life	At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.
Safety	This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments,direct sunshine and out of children's reach.  Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.