



# RTB-888-R (A&B COMPONENTS)

High-Performance two-component flexible mastic with excellent adhesion, sealing, and filling properties along with exceptional seawater resistance. This product has been developed to perform under external pressure and tensile forces.

#### **USES AND SUITABLE PRIMERS**

Recommended Uses Ronass Flexi Mastic is designed for application on interior or exterior sides of properly prepared steel, rubber,

concrete or plastic surfaces. This multi-purpose product is very useful when used with bondage or tape to plug

leakages.

Suitable Primers Epoxy primers or sealers if applicable.

## PHYSICAL PROPERTIES

Finish Semi Flat Colour Black

Specific Gravity after Mixing  $1.75 \pm 0.05$  gr/cm<sup>3</sup> Viscosity High Viscous Paste

#### **APPLICATION DETAILS**

Surface Preparation All oil, grease, dirt and other contaminants must be removed from the surface.

Concrete surfaces must be dried, cleaned and treated with an epoxy sealer.

Steel surfaces should be sandblasted according to Swedish Standard (SIS 5900). Sa 2 ½ or greater.

Rubber and plastic surfaces must be thoroughly cleaned.

Mixing Ratio Component A: 100 Parts by weight Component B: 15 Parts by weight

Mixing Instructions Mix component A thoroughly with a suitable mixer for 10 minutes, then add component B slowly and mix well for 5

additional minutes, making sure a consistent mixture is obtained.

Pot Life 45 Minutes at 25°C

Theoretical Consumption 1750 gr/m² @ 1 mm DFT
Thinning Never thin down the product

Method of Application Use a special knife, spatula, trowel or gloved hand to apply the product. If adhering two surfaces is required, apply

Ronass Flexi Mastic on both surfaces, and press together. Due to the high viscosity of the paste, pre-heating the

product before use is recommended to obtain better flow characteristics.

Film Thickness

	Recommended	Minimum	Maximum
Film Thickness (mm)	Depends on Surface Conditions	0.5	

 Drying Time
 Dry Hard
 Fully Cured

 24 Hours
 21 Days

**Application Limits** 

Relative Humidity	Min	Max. 80%
Temperature	Min. +5°C	Max. +40°C
Substrate Temperature*	Min. +5°C	Max. +45°C

<sup>\*</sup>Please note that the substrate temperature should be at least 5°C above the dew point

Recommendations Clean tools thoroughly before and immediately after use with T-445.

## PACKING, STORAGE AND SAFETY

Packing Component A (Base): 4 Litres Containers (5 kgs. Net) and Component B(Hardener): 1 Litres Containers (0.750 kgs. Net)

Storage Conditions To be stored in cool and dry conditions in original sealed containers.

Shelf Life At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.

Safety This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and

equipments, direct sunshine and out of children's reach.

Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.















