

A surface-tolerant coating based on epoxy polyamide, anti-corrosive pigments, and inhibitor penetrating agents with excellent adhesion, internal binding and penetration properties.

### USES AND SUITABLE TOP-COATS

Recommended Uses	Can be used as a sealer and intermediate coat for steel structures and primed metal surfaces as an excellent holding primer particularly when fresh sandblasted surfaces have slightly rusted or the recoating interval has expired.
Suitable Top-Coats	RTB-927 can be over-coated by all types of epoxy and polyurethane coatings.

### CHEMICAL COMPOSITION

Type of Binder	Epoxy – Polyamide	Solid Content After Mixing	65 ± 1% By Weight
Number of Component(s)	2 Components		46 ± 2% By Volume
Curing Mechanism	Chemical Reaction	Flash Point	28°C (82°F)

### PHYSICAL PROPERTIES

Finish	Semi flat
Colour	Cream (RAL-9001)
Specific Gravity after Mixing	1.30 ± 0.05 gr/cm <sup>3</sup>

### APPLICATION DETAILS

Surface Preparation	All oil, grease, dirt and other contaminants must be removed from the surface. Mechanical surface preparation according to the surface condition is recommended.
Mixing Ratio	Component A: 100 Parts by weight    Component B: RTB-927-B or RTB-9700 25 Parts by weight
Mixing Instructions	Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 5 minutes. Keep the mixture for 10 additional minutes prior to thinning down to allow for the pre-reaction time. Do not thin down each component separately.
Pot Life	8 Hours at 25°C
Theoretical Consumption	56 gr/m <sup>2</sup> @ 20 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.009" – 0.011"	1.80 mm	---	---
	Pump Ratio	1 / 28	---	---	---
	Air Pressure	3 – 5 Bar	3 – 4 Bar	---	---
	Thinning	5 – 10% T-445	10 – 20% T-445	5 – 10% T-445	5 – 10% T-445

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	30	10	60
	Dry Film Thickness (µm)	15	5	30

Drying Time	Dust Free Time	Tack Free Time	Dry to Handle	Recoating Interval
	30 – 45 Minutes	1 – 2 Hours	3 – 4 Hours	Min. 8 Hours Max. 10 Days

*\*Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +5°C	Max. +40°C
	Substrate Temperature*	Min. +5°C	Max. +45°C

*\*Please note that the substrate temperature should be at least 5°C above the dew point*

Recommendations	-Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet. -Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-445.
-----------------	---

### PACKING, STORAGE AND SAFETY

Packing	Component A(Epoxy): 20 Litres Containers (20 kgs. Net) and Component B(Hardener): 10 Litres Containers (5 kgs. Net)
Storage Conditions	To be stored in cool and dry conditions in original sealed containers.
Shelf Life	At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.
Safety	This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach.  Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.