



# RONASS HIGH-BUILD EPOXY POLYAMINE COATING

## RTB-979 (A&B COMPONENTS)

A high-build, high-solid surface-tolerant epoxy coating with excellent adhesion and anti-corrosive properties. This coating also has great raw water, fuel and chemical resistances.

### USES AND SUITABLE PRIMERS

**Recommended Uses** Intermediate and, finish coat or self-priming system for water, chemicals and fuel tanks, steel structures, maintenance operations and protective coating systems. This coating can also be used as a finish coat for epoxy coating systems on concrete surfaces.

**Suitable Primers** Organic and inorganic Zinc-rich primers, M.I.O. epoxies and other high build epoxy coatings and primers.

### CHEMICAL COMPOSITION

Type of Binder	Epoxy – Polyaminoamide	Solid Content After Mixing	80 ± 1% By Weight
Number of Component(s)	2 Components		62 ± 2% By Volume
Curing Mechanism	Chemical Reaction	Flash Point	28°C (82°F)

### PHYSICAL PROPERTIES

**Finish** Semi flat  
**Colour** White Pure (RAL-9010) – Light Grey (RAL-7035) – Silver Grey (RAL-7000).  
**Specific Gravity after Mixing** 1.60 ± 0.10 gr/cm<sup>3</sup>

### APPLICATION DETAILS

**Surface Preparation** All oil, grease, dirt and other contaminants must be removed from the surface. Sandblast according to Swedish Standard(SIS 5900). Sa 2 ½ or Sa 3 is recommended.

**Mixing Ratio** Component A: 100 Parts by weight      Component B: RTB-979-B or RTB-9400 10 Parts by weight

**Mixing Instructions** Mix component A thoroughly with a suitable mixer, then add component B slowly and mix well for 5 minutes. Keep the mixture for 10 additional minutes prior to thinning down to allow for pre-reaction time. Do not thin down each component separately.

**Pot Life** 2 Hours at 25°C

**Theoretical Consumption** 260 gr/m<sup>2</sup> @ 100 Microns DFT

Paint Application	Methods	Airless Spray	Air Spray	Brush	Roller
	Nozzle Size	0.011" – 0.015"	1.80 mm	---	---
	Pump Ratio	1 / 45	---	---	---
	Air Pressure	4 – 6 Bar	3 – 4 Bar	---	---
	Thinning	5 – 10% T-445	10 – 15% T-445	3 – 5% T-445	3 – 5% T-445

Film Thickness		Recommended	Minimum	Maximum
	Wet Film Thickness (µm)	160	95	280
	Dry Film Thickness (µm)	100	60	175

Drying Time	Dust Free Time	Tack Free Time	Dry to Handle	Fully Cured	Recoating Interval
	45 – 60 Minutes	3 – 4 Hours	16 – 24 Hours	7 – 10 Days	Min. 16 Hours Max. 10 Days

*\*Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT*

Application Limits	Relative Humidity	Min. ---	Max. 80%
	Temperature	Min. +10°C	Max. +40°C
	Substrate Temperature*	Min. +10°C	Max. +45°C

*\*Please note that the substrate temperature should be at least 5°C above the dew point*

**Recommendations** -Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.  
 -Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-445.

### PACKING, STORAGE AND SAFETY

**Packing** Component A(Epoxy): 20 Litres Containers (25 kgs. Net) and Component B(Hardener): 5 Litres Containers (3.750 kgs. Net)

**Storage Conditions** To be stored in cool and dry conditions in original sealed containers.

**Shelf Life** At least 18 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.

**Safety** This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and equipments, direct sunshine and out of children's reach.  
 Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.

