

RONASS HEAT-RESISTANT COATING (UP TO 200°C)

RTB-990-R

Medium range heat-resistant coating with excellent adhesion and anti-corrosive properties.

USES AND SUITABALE PRIMERS

Recommended Uses Finish coat for steel structures and metal surfaces which are subjected to medium thermal stresses up to 250°C.

Suitable Primers RTB-721-R (Ronass Heat Resistant Primer) or other medium-range heat-resistant primers.

CHEMICAL COMPOSITION

Type of Binder Silicone-Modified Acrylic Resin Solid Content Silver Other Colours Number of Component(s) 1 Component By Weight $50 \pm 1\%$ $65 \pm 1\%$ **Curing Mechanism** Thermosetting By Volume 41 ± 2% $45 \pm 2\%$

Flash Point 28°C (82°F)

PHYSICAL PROPERTIES

Finish Semi aloss

Colour White Aluminum (RAL 9006), Pure White (RAL-9010), Squirrel Grey (RAL-7000), Jet Black (RAL-9005)

Specific Gravity (Silver): 1.00 ± 0.03 gr/cm³ | (Other Colours): 1.35 ± 0.10 gr/cm³

Heat Resistance Continuous Service: 200°C

Non-Continuous Service: 250°C

*Please note that this coating's colour and Gloss may changed when subjected to high temperatures. These minor

changes do not effect on performances of the paint's film.

APPLICATION DETAILS

Surface Preparation All oil, grease, dirt and other contaminants must be removed from the surface. Wire brush or sandblast according to

the Swedish Standard (SIS 5900). Sa 2 and treatment with Ronass heat- resistant primer, RTB-721-R is highly

recommended

Theoretical Consumption

100-120 gr/m² @ 40 Microns DFT

Paint Application

Methods	Airless Spray	Air Spray	Brush	Roller
Nozzle Size	0.009" - 0.011"	1.80 mm		
Pump Ratio	1 / 28			
Air Pressure	4 – 6 Bar	3 – 4 Bar		
Thinning	5 – 10% T-991	10 – 20% T-991	3 – 5% T-991	3 – 5% T-991

Film Thickness

	Silver	Other Colours
Wet Film Thickness (µm)	60 – 85	60 – 110
Dry Film Thickness (µm)	25 – 35	30 – 50

Drying Time

Dust Free Time	Tack Free Time	Fully Cured	Recoating Interval
20 – 30 Minutes	60 – 90 Minutes	In Service	Min. 24 Hours Max *

Drying time calculated at 25°C according to ASTM test method D-1640 for 100 µm WFT

*Please note that once Heat-Resistant coatings have been exposed to service condition, prior torecoating and paint application, surface preparation including cleaning, degreasing, and gentle scrubbing with a suitable sandpaper is recommended.

Application Limits

Relative Humidity	Min	Max. 80%
Temperature	Min. +5°C	Max. +40°C
Substrate Temperature*	Min. +5°C	Max. +45°C

Please note that the substrate temperature should be at least 5°C above the dew point

Recommendations

-Should the recoating interval have expired, please refer to the procedures outlined in the Ronass Instruction Leaflet.

-Clean tools thoroughly before and immediately after use with cleaning solvent T-111 or T-991.

PACKING, STORAGE AND SAFETY

Packing 10 Litres Containers (10 kgs. Net)

Storage Conditions To be stored in cool and dry conditions in original sealed containers.

Shelf Life At least 12 months after delivery in original sealed containers and proper storage conditions with temperature of 25°C.

This product contains organic solvents and flammable materials. Keep away from sparks, fires, electrical cables and Safety

equipments, direct sunshine and out of children's reach.

Protect skin, eyes, and avoid prolonged breathing of solvent vapor during application. Use with adequate ventilation.

















